


# Biodegradable Polyester

Under the tests conducted in a landfill environment (ASTM D5511) and in a marine environment (ASTM D6691), the mechanism of biodegradation was activated until the fiber was fully degraded.



- Landfill environment (ASTM D5511) test method: biodegradation rate was 91% within 1278 days
- Marine environment (ASTM D6691) test method: biodegradation rate was 44.5% within 262 days

